

DIRECT TO FILM TRANSFERS

ULTRACOLOR[®]

MAX


APPLICATION INSTRUCTIONS:



12–15 seconds



290°F / 145°C



Medium



Hot

NOTE: Yellowing of the adhesive or waffle texture on the carrier is possible and normal. This will not affect heat application.