# ORACAL 352 Print Polyester

## **Description**

Transparent, white or metallized polyester film with excellent dimensional stability and good long- term ageing properties. Surface with top-coat for printing.

### Release paper

PE-coated release paper on both sides, 160 g/m<sup>2</sup>.

#### **Adhesive**

Solvent polyacrylate, permanent

### Area of use

For first class decorative labels, name and technical plates, decoration and moldings, safety stickers.

#### **Printing method**

Screen printing and UV-offset printing are recommended.

#### **Technical data**

1 centileur datu	
Thickness* (without protective paper and adhesive)	23 micron (transparent, chrome, matt chrome, gloss gold, gloss gold on both sides) 50 micron (white, chrome, brushed silver, gloss gold on both sides)
<b>Dimensional stability</b> (FINAT TM 14)	adhered to steel, no measurable shrinkage in cross direction, in length 0.10 mm max.
Temperature resistance	adhered to aluminium, -40°C to +120°C, no variation
Seawater resistance (DIN 50021)	adhered to aluminium, after 100h/23°C no variation
Adhesive power*	12 N/25 mm
(FINAT TM 1, after 24h, stainless steel)	
<b>Tensile strength</b> (DIN EN ISO 527)	
along	min. 200 MPa
across	min. 260 MPa
Elongation at break (DIN EN ISO 527)	
along	min. 125%
across	min. 80%
Shelf life**	2 years
Application temperature	>+8°C
Service life by specialist application under vertical outdoor exposure (normal climate of Ce	2 years, glossy gold 1 year (not printed) entral Europe)

<sup>\*</sup> average \*\* in original packaging, at 20°C and 50% relative humidity

#### **Attention:**

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure respectively. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore the application information published by ORAFOL is to be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.

